
Docket No.: TOW-032

App No.: NEW APPLICATION Docket Inventor: Teruaki Komiya
Title: PROTON CONDUCTIVE SOLID POLYMER ELECTROLYTE

1/3




Docket No.: TOW-032

App No.: NEW APPLICATION Docket Inventor: Teruaki Komiya
Title: PROTON CONDUCTIVE SOLID POLYMER ELECTROLYTE

2/3

FIG. 2



Docket No.: TOW-032

App No.: NEW APPLICATION Docket Inventor: Teruaki Komiya
Title: PROTON CONDUCTIVE SOLID POLYMER
ELECTROLYTE

3/3

FIG. 3

	MOLE NUMBER OF PHOSPHORIC ACID PER REPEATING UNIT OF PBI IN MEMBRANE	MOLE NUMBER OF IMIDAZOLE PER GRAM OF PBI (mol/g)	PROTON CONDUCTIVITY (S/m)	RATIO OF IMPROVEMENT IN PROTON CONDUCTIVITY (%)
COMPARATIVE EXAMPLE	12. 9	0	0. 100	- -
EXAMPLE 1	12. 7	0. 00012	0. 127	27
EXAMPLE 2	12. 9	0. 00025	0. 133	33
EXAMPLE 3	12. 9	0. 00051	0. 113	13